



Underbody Protection Bitumen

product information

16-05-2022 V1

Side 1 von 1

AP-Merit underbody protection bitumen is a durable wax/bitumen-based rust protection for vehicle floors, entrance and wheel housings, etc.. Good anti-drumming effect, very good adhesion, elastic, tack-free, high abrasion resistance and good road salt resistance.

Color	black									
Dilution	Ready for use									
Application process	<table border="1"><thead><tr><th>Spray gun</th><th>Spray pressure</th><th>Nozzle size</th></tr></thead><tbody><tr><td>UBS-Gun</td><td>4 - 6 bar</td><td>5 - 10 mm</td></tr><tr><td>Airmix / Airless</td><td>100 - 120</td><td>0,33 - 0,5 mm</td></tr></tbody></table>	Spray gun	Spray pressure	Nozzle size	UBS-Gun	4 - 6 bar	5 - 10 mm	Airmix / Airless	100 - 120	0,33 - 0,5 mm
Spray gun	Spray pressure	Nozzle size								
UBS-Gun	4 - 6 bar	5 - 10 mm								
Airmix / Airless	100 - 120	0,33 - 0,5 mm								
Drying	Set to touch: 2-4 hours / 20°C									
Flash-off time	5 - 8 minutes between spraying									
Spray application	1-2 spray coats (dry film thickness 500-1000 µm), consumption approx. 1-2 m ² /lt.									
VOC Regulation	EU limit value for this product (category B/e): 840 g/l This product contains max. 840 g/l of VOC.									

Processing instructions:

After brief shaking, the product is sprayed evenly onto the surface in a cross pattern. The surface texture can be influenced by changing the air pressure and spraying distance. Vehicle floor must be thoroughly cleaned and dry, free from dust, grease, oil and rust. Underbody protection cannot be painted over!

Old, no longer adhering underbody protection must be removed.

Do not spray on engine, transmission, oil pan, cardan shaft, exhaust, axles, springs, shock absorbers, brake cables, grease nipples etc., cover beforehand!

Processing conditions:

Ensure sufficient supply and exhaust air. Processing temperature at least +10 °C. Maximum air humidity 80 %.

Storage and shelf life:

Store the product in a ventilated place. Protect from direct sunlight. Store between +5 °C and 25 °C. Shelf life at least 12 months.

This product sheet is for information purposes only ! To the best of our knowledge, the information given here corresponds to the state of the art and is based on many years of experience in the manufacture of our products. However, the information is nonbinding and without guarantee.